



ROWAFLON G-71004

- APPLICATION :**
- Textile constructions
 - Tent roof
 - Truck cover

TECHNICAL DATA :

- Delivery form :** Solution, opaque
Solid content - % : 10,6 ± 0,5
Viscosity - mPas : 250 ± 80
Resin system : Acrylic modified Fluoropolymer
Solvents included : Methyleneethylketone, Dimethylformamide

- CHARACTERISTICS :**
- Minimal soiling tendency
 - Abrasion resistant
 - Anti-blocking
 - Dirt resistant
 - Weather resistant
 - HF-weldable
 - High gloss
 - Flexible
 - Easy cleanable

- PROCESSING :**
- Stir well before use!
 - Filter before application!

- Film thickness - g/m² dry :**
- 4-6

- Drying process :**
- 1 min / 130-150°C

- Application methods :**
- Rotogravure
 - Magnet bar

- Diluent :**
- Methyleneethylketone
 - DMF

- Storage :**
- Dry
 - Room temperature
 - Original pack
 - Air-tight closed

- Shelf life :**
- 6 months (closed original pack)

Stand: 17.08.2006 / IN
30.05.2007 / IN