



ROWAFLON G-73997

**Technisches Merkblatt
Technical Report**

Distributed by



APPLICATION : • UV protection primer • Textile constructions

TECHNICAL DATA :

Form supplied :	Solution, white
Solid content - % :	15.0 ± 0.5
Viscosity - mPas :	100 ± 50
Gloss ∠ 60° :	45 ± 5
Resin system :	Fluoropolymer, Acrylic
Solvents included :	Methylethylketone, Dimethylformamide

CHARACTERISTICS :

- Weather resistant
- UV protection
- Excellent adhesion on soft PVC
- **Not useable as top coat**

PROCESSING :

- **Stir very well before use !**
- **Filter before application !**

Film thickness - g/m² dry : • 5 -7

Drying process : • 1 min / 130-150°C

Application methods : • Rotogravure • Magnet bar

Diluent : • Methylethylketone • Dimethylformamide

Storage :

- Dry
- Room temperature
- Original pack
- Air-tight closed

Shelf life : • 1 months (closed original pack)

Stand: 28.09.2006 / HR 30.05.2007 / IN
21.08.2008 / PO