



**Technisches Merkblatt
Technical Report**

Distributed by



ROWAKRYL G-32237

APPLICATION:

- Backlit
- Material for advertising
- Frontlit

TECHNICAL DATA:

Delivery form:	Solution, colourless
Solid content - %:	15.6 ± 0.5
Viscosity - mPas:	200 ± 100
Resin system:	Acrylic, PVC
Solvents included:	Methylethylketone, Acetone, MP, Tetrahydrofuran

CHARACTERISTICS:

- Printable
- HF-weldable
- Good lightfastness
- Abrasion resistant
- Exact, clear printing
- Flexible
- Non-blocking

PROCESSING:

- **Stir well before use!**
- **Filter before application!**

Film thickness - g/m² dry: • 4-6

Drying process: • 1 min / 100°C

Application methods: • Rotogravure • Magnet bar

Diluent: • Ketones • Esters
 • DMF, NMP, THF

Storage: • Dry • Original pack
 • Room temperature • Air-tight closed

Shelf life: • 6 months (closed original pack)

Stand: 01.10.1998 / FN
 19.04.2007 / PO