



ROWAKRYL G-31208

APPLICATION:

- Heavy tarpaulin
- Awnings
- Textile constructions
- Material for tent-roofs

TECHNICAL DATA:

| | |
|--|------------------------------|
| Delivery form: | Solution, colourless, opaque |
| Solid content - %: | 13.7 ± 0.5 |
| Viscosity - mPas: | 250 ± 50 |
| Blocking resistance: (80°C - N/cm) | < 0.1 |
| Resin system: | Acrylic, PVC |
| Solvents included: | Methylethylketone, DMF, THF |

CHARACTERISTICS:

- Abrasion resistant
- HF-weldable
- Light resistant
- Flexible
- Weather resistant
- Excellent cleanability
- Low surface friction
- hard surface

PROCESSING:

- Stir well before use !
- Filter before application !

Film thickness - g/m² dry: • 5-6

Drying process: • 1 min / 100-120°C

Application methods: • Rotogravure • Magnet bar

Diluent: • Ketones • Ester
• Aromatic solvents (blendable)

Storage: • Dry • Original pack
• Room temperature • Air-tight closed

Shelf life: • 6 months (closed original pack)

Stand: 29.09.05 / PO
28.06.07 / IN