



ROWAKRYL G-33230

APPLICATION:

- Backlit
- Material for advertising
- Frontlit

TECHNICAL DATA:

Delivery form:	Solution, opaque
Solid content - %:	14,5 ± 0,5
Viscosity - mPas:	300 ± 100
Resin system:	Acrylic, PVC
Solvents included:	Methylethylketone, Toluene, DMF

CHARACTERISTICS:

- Printable
- HF-weldable
- Light resistant
- Good plasticizer barrier
- Exact, clear printing
- Flexible
- Abrasion resistant

PROCESSING:

- **Stir well before use!**
- **Filter before application!**

Film thickness - g/m² dry: • 6-8

Drying process: • 1 min / 100°C

Application methods: • Rotogravure • Magnet bar

Diluent: • Ketones • Esters
• Aromatic solvents (blendable)

Storage: • Dry • Original pack
• Room temperature • Air-tight closed

Shelf life: • 6 months (Closed original packaging)

Stand: 16.02.2002 / PO
10.12.2007 / IN