



ROWAKRYL G-33632

APPLICATION:

- Truck cover
- Awnings
- PVC-tarpaulins

TECHNICAL DATA:

Delivery form:	Solution, opaque
Solid content - %:	15,0 ± 0,5
Viscosity – mPas:	130 ± 50
Resin system:	Acrylic, PVC
Solvents included:	Methylethylketone, Dimethylformamide, Toluene, Acetone

CHARACTERISTICS:

- Medium hard
- Flexible
- Good slip properties
- Minimal soiling tendency
- Weather resistant
- HF-weldable
- High gloss
- Abrasion resistant

PROCESSING:

- Stir well before use !
- Filter before application !

Film thickness - g/m² dry: 5-6

Drying process: 1 min / 100-120°C

Application methods: • Rotogravure • Magnet bar

Diluent: • Ketones • Esters
• DMF • NMP
• Aromatic solvents (blendable)

Storage: • Dry • Original pack
• Room temperature • Air-tight closed

Shelf life: • 6 months (closed original pack)

Update: 03.02.05 / PO
03.07.07 / IN