



**Technisches Merkblatt
Technical Report**

Distributed by



ROWAKRYL G-34049

APPLICATION:

- Backlit
- Material for advertising
- Frontlit

TECHNICAL DATA:

Delivery form:	Solution, colourless
Solid content - %:	13.5 ± 0.5
Viscosity - mPas:	100 ± 50
Gloss 60°:	approx. 90
Resin system:	Acrylic, PVC
Solvents included:	Methylethylketone, Dimethylformamide

CHARACTERISTICS:

- Printable
- HF-weldable
- Glossy surface
- Abrasion resistant
- Brilliant printing
- Hard
- Low surface friction

PROCESSING:

- Stir well before use !
- Filter before application !

Film thickness - g/m² dry: • 5-7

Drying process: • 1 min / 100°C

Application methods: • Rotogravure • Magnet bar

Diluent: • Ketones

Storage: • Dry • Original pack
• Room temperature • Air-tight closed

Shelf life: • 6 months (closed original packaging)

Update : 12.03.07 / IN
30.05.07 / IN