



**Technisches Merkblatt
Technical Report**

Distributed by



ROWAKRYL G-34104W

APPLICATION:

- Truck cover
- Heavy tarpaulin
- Awnings

TECHNICAL DATA:

Delivery form:	Dispersion, water-borne, white
Solid content - %:	23.0 ± 1.0
Discharge time - s: (4mm DIN cup)	30.0 ± 5.0
pH-value:	8.5 ± 0.5
Gloss ∠ 60°:	50.0 ± 10.0
Resin system:	Acrylic / Polyurethane Copolymer
Solvents included:	Water, EDG, IPA

CHARACTERISTICS:

- Easy weldable
- Non-blocking
- Easy cleanable
- Flexible
- Weather resistant

PROCESSING:

- **Stir well before use!**
- **Filter before application!**

Film thickness - g/m² dry: • 5-6

Drying process: • 1 min / 120°C

Application methods: • Rotogravure • Magnet bar

Diluent: • Water

Storage: • Room-temperature • Airtight closed
• Keep from frost • Keep from heat

Shelf life: • 6 month (closed original pack)

Stand: 05.12.2007 / KD

Alle Angaben stützen sich auf den heutigen Stand unserer Kenntnisse. Sie zeigen unverbindlich die Anwendungsmöglichkeiten unserer Produkte

Data are based on tests known to be reliable. They are given for information only, as we cannot guarantee the results of operations not under our direct control.