



**Technisches Merkblatt
Technical Report**

Distributed by



ROWAKRYL G-34110

APPLICATION :

- Furniture sheets
- Gloss version of ROWAKRYL M-34108

TECHNICAL DATA :

Form supplied :	Solution, colourless, opaque
Solid content - % :	30,0 ± 1,0
Viscosity - s : (4 mm DIN cup / supplied form)	22,0 ± 5,0
Resin system :	Acrylic, modified PVC, crosslinkable
Crosslinker :	ROWASET 61117
Mixing ratio - g :	100 : 10 / lacquer : crosslinker
Gloss at 60° :	90,0 ± 10,0
Pot life - h :	> 8
Solvents included :	Methyl ethyl ketone, Acetone, Methoxy propyl acetate

CHARACTERISTICS :

- Two-pack system
- Flexible
- Chemical resistant
- Matt
- Scratch resistant
- Fast drying

PROCESSING :

- Stir well before use !
- Filter before application !

Drying process : 60 s / 80 - 100°C

Film thickness - g/m² dry : 4 - 6

Crosslinker : Rowaset 61117 (100 g lacquer : 10 g crosslinker)

Application methods :

- Rotogravure
- Magnet bar

Diluent :

- Ketones
- Aromatic solvents
- Esters

Storage :

- Dry
- Room temperature
- Original pack
- Air-tight closed

Shelf life : 6 months (closed original pack)

Update: 03.01.08 / IN