



**ROWAKRYL M-33360W**

**APPLICATION:**

- PVC-tarpaulin
- Material for advertising

**TECHNICAL DATA:**

<b>Form supplied:</b>	Dispersion, waterborne, white
<b>Total solids - %:</b>	23.0 ± 1.0
<b>Viscosity - s:</b> (4mm DIN-cup)	19.0 ± 3.0
<b>Gloss ∠ 60°:</b>	6.0 ± 1.5
<b>Resin System:</b>	Polyurethane, Acrylic, PVC
<b>Solvents included:</b>	Water, EDG

**PROPERTIES:**

- Flexible
- Slip
- Non-blocking
- Silk gloss
- HF-weldable
- Printable

**PROCESSING:**

- **Mix well before use!**
- **Filter before application!**

**Drying requirement:**

- 1 min / 120°C

**Film thickness - g/m<sup>2</sup> dry:**

- 4 - 6

**Application methods:**

- Rotogravure
- Magnet bar

**Additives:**

- ROWASET 61521W (wetting agent)
- ROWASET 61247W (defoamer)
- ROWASET 61542W (thickener)

**Storage:**

- Air-tight closed
- Keep from freezing
- Original pack
- Keep from heating

**Shelf life:**

- 6 month (closed original pack)

Stand: 20.10.2005 / PO  
23.04.2007 / PO