



**ROWAKRYL M-33575**

**APPLICATION:**

- PVC-tarpaulin
- Army cover

**TECHNICAL DATA:**

<b>Delivery form:</b>	Solution, whitish, opaque
<b>Solid content - %:</b>	14.0 ± 0.5
<b>Viscosity - mPas:</b>	120 ± 30
<b>Gloss ∠ 60°:</b>	1.0 ± 0.5
<b>Resin system:</b>	Acrylic, PVC
<b>Solvents included:</b>	MEK, Toluene, DMF, Acetone

**CHARACTERISTICS:**

- Medium-hard
- HF-weldable
- Weather resistant
- Extreme matt
- Flexible
- Bendable

**PROCESSING:**

- **Stir very well before use!**
- **Filter before application!**

**Film thickness - g/m<sup>2</sup> dry:**

- 4-6

**Drying process:**

- 1 min / 100°C

**Application methods:**

- Rotogravure
- Magnet bar

**Diluent:**

- Ketones
- Esters
- Aromatics (blendable)

**Storage:**

- Dry
- Room temperature
- Original pack
- Air-tight closed

**Shelf life:**

- 6 months (closed original pack)

Stand: 09.09.2003 / PO  
20.07.2007 / PO